



2-001

Eco binder Aqua 2G

Resin **2-001** is an additive that, when used in conjunction with **Aqua 2G** basecoat, helps create an economical and efficient paint mix. This innovative product has been formulated to ensure that the addition of resin does not negatively impact the colour match of the paint.

However, it's important to note that the addition of resin may slightly reduce the covering power of the basecoat. Therefore, it's essential to consider this factor when applying the mixture. Furthermore, it's crucial to avoid adding any thinners to the paint/resin mixture, as this may affect the quality of the final result. Resin **2-001** is available in convenient 5-litre tins, making it an ideal choice for professionals and DIY enthusiasts alike who require a high-quality, reliable additive to improve the performance of their paint.

PACKAGING	
Volume	Collective packaging
5 l	4 pcs.



NO COLOUR
CHANGE



NO SIGNIFICANT
IMPAIRMENT TO
COVERING POWER



ENVIRONMENTALLY
FRIENDLY



EFFICIENT



SPRAY VISCOSITY
10-12 sec. DIN Flow Cup 4 mm



**RECOMMENDED SIZES
FOR PAINT STRAINER**
125 µm



PAINT EFFICIENCY
8-9 m²/l



POT LIFE
Product ready for spraying



DRY FILM THICKNESS
1 coat - 5-10 µm



MINIMUM SHELF LIFE
24 months in originally sealed packaging



VOC
2004/42/WE/IIIB(d)(420) 383

PROCESS

PROCESS

PROCESS



SUBSTRATE PREPARATION
Once the suitable primer coat has been abraded, clean using silicone remover **CP 15** in preparation to apply basecoat



MIXING RATIO
100 parts of Aqua 2G
10-30 parts of 2-001

In case of adding **2-001**, do not add any amount of thinner



SPRAY GUN SETTINGS
Nozzle size: **1.2-1.4 mm**;
Operating pressure: HVLP/RP **1.8-2.0 bar**



APPLICATION
Control coat first, then application of full poured coat.
For solid colours this is the end of the process, effect colours require an additional coat on reduced pressure



**EVAPORATION TIME
AFTER APPLICATION**
15-20 min. after coating at **20°C**
and **65%** relative humidity