



CP 999

Fade out binder

The resin, a one-component formulation tailored for vehicle bodywork, serves a specific purpose: to harmonize colour disparities between the **Kar-Bon/Green-Line** basecoat used and the existing basecoat on adjacent areas during local touch-ups.

After the application of the **CP 999** resin coat, a layer of shaded **Kar-Bon/Green-Line** basecoat is applied wet-on-wet. The unique properties of **CP 999** ensure a seamless transition without any visible "clouding" at the border, rendering the shade difference invisible.

Available in 1-Litre tins, this product provides a precise solution for localized colour adjustments, maintaining a flawless finish in automotive bodywork

PACKAGING	
Volume	Collective packaging
1 l	3 pcs.



EFFICIENT



NO SANDING
REQUIRED



SMOOTH SURFACE



EASY TO APPLY



SPRAY VISCOSITY

17-19 sec. DIN Flow Cup 4 mm



RECOMMENDED SIZES FOR PAINT STRAINER

125-190 µm



POT LIFE

Product ready for spraying



DRY FILM THICKNESS

1 coat - 10 µm



MINIMUM SHELF LIFE

24 months in originally sealed packaging



VOC

2004/42WE/IIIB(e) (840) 707



SUBSTRATE PREPARATION

Degrease the surface, matt the old coatings with a grey or golden fleece, preferably, with a matt polish



MIXING RATIO

100 parts of **CP 999**
100 parts of thinner
CP 048/ CP 078/ CP 055



SPRAY GUN SETTINGS

Nozzle size: **1.2-1.4 mm**;
Operating pressure: HVLP/RP **1.8-2.0 bar**



APPLICATION

1-2 coats on the surface before shading with basecoat. Apply the basecoat immediately after the resin application in order to prevent the resin coat from drying out

PROCESS

PROGRESS